

AMENDMENTS

IN THE CLAIMS:

Please add new claims 10-15 as follows:

10. The manufacturing method of the polarizing film according to claim 5, wherein the pressurization is performed at not less than 20 N/cm.

11. The manufacturing method according to claim 1, wherein the polarizing film comprises at least two layers having different softening points.

AI 12. The manufacturing method according to claim 11, wherein a softening point of a layer having a low softening point is not less than 80°C.

13. The manufacturing method according to claim 11, wherein a softening point of a layer having a low softening point is not less than 90°C.

14. The manufacturing method according to claim 11, wherein a difference between softening points of the layers is not less than 5°C.

15. The manufacturing method according to claim 11, wherein a difference between softening points of the layers is not less than 10°C.